

TECHNICAL DATA SHEET

KEPSTAN® 6010G30

KEPSTAN® 6010G30 resin is a glass fiber reinforced compound, based on the 6000 series of KEPSTAN® resins.

KEPSTAN® 6010G30 resin is a glass fiber reinforced compound, based on the 6000 series of KEPSTAN® resins. This series represents the pseudo-amorphous products of the KEPSTAN® family, offering the lowest melting point and the slowest crystallization behavior, while keeping Tg close to 160°C. These properties allow for lower processing temperatures and lead to glassy or semi-crystalline structures, depending on processing technologies and cooling conditions.

KEPSTAN® 6010G30 resin is a low flow grade, suitable for extrusion, compression and injection molding.
KEPSTAN® 6010G30 resin is available in pellet form and standard packaging is 20 kg boxes.

PRODUCT PERFORMANCE

SUGGESTED APPLICATIONS

SHELF LIFE

Store in the original, closed container in a dry, cool (<45°C) and well-ventilated place. Keep away from frost and heat (open flames, hot surfaces and sources of ignition) sources. Typical shelf-life is months from delivery date for unopened containers. In cases where product sampling is required to carry out incoming quality tests, shelf-life should be maintained beyond opening, provided that it is tightly closed immediately after and that contamination with foreign bodies is avoided.

Inhibitors have been added to enhance storage stability. They require the presence of air in the container in order to improve their efficiency. Keep stabilizer levels constant to avoid explosive polymerization. An air space is required above the liquid in all containers

STORAGE

See SDS for Storage Considerations

HEALTH AND SAFETY

See SDS for Health & Safety Considerations

Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex
France
www.Sartomer.arkema.com