

TECHNICAL DATA SHEET

KYNAR FLEX[®] 2800-20

FLUORINATED COPOLYMER PELLET

KYNAR FLEX[®] resins are fluorinated thermoplastic copolymers. Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermo-mechanical properties. This product is NSF/ANSI/CAN 61 certified. KYNAR FLEX[®] resin is a standard grade of granules, compared to the homopolymer grades, which exhibits a lower modulus, a better resistance to stress cracking in alkaline and oxidizing media, and a lower melting point. For cable coating, extrusion of tube and plaque, injection molding.

- Additional characteristics:
- Easily processed using conventional equipment
 - Excellent thermal stability
 - Retains properties after aging
 - Pigmentable
 - UL RTI temperature rating 125°C

TYPE	배송 방식
PVDF	• 펠릿
MAIN APPLICATIONS	가공 공정
• 분체 도장 - 기타	• 사출성형
• 튜브	
• 플레넘 파이프	

RHEOLOGICAL PROPERTIES

속성	값	UNIT	테스트 표준
Melt viscosity, 230°C (445°F) at 100 s-1	12 - 20	kPo	ASTM D3835
Melt flow index (MFR), 235°C / 5 kg (455°F / 11 lb)	1 - 8	g/10min	ASTM D1238
Melt volume flow rate (MVR), 230°C / 5 kg (446°F / 11 lb)	4.5	cm³/10min	ISO 1133

MECHANICAL PROPERTIES

속성	값	UNIT	테스트 표준
Yield stress, 23°C (73°F)	20 - 34.5	MPa	ASTM D638
Stress at break, 23°C (73°F)	17.2 - 34.5	MPa	ASTM D638
Compression strength, 23°C (73°F)	31 - 41.4	MPa	ASTM D695
Izod impact unnotched strength, 23°C (73°F)	No Break		ASTM D256
Izod impact notched strength, 23°C (73°F)	0.534 - 1.07	J/m	ASTM D256
Charpy unnotched impact strength, 23°C (73°F)	177	kJ/m2	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	235	kJ/m2	ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	60	kJ/m2	ISO 179 1eA

KYNAR FLEX® 2800-20

속성	값	UNIT	테스트 표준
Charpy notched impact strength, -30°C (-22°F)	5	kJ/m2	ISO 179 1eA
Hardness, Shore D	60 - 70		ASTM D2240
Nominal strain at break, 23°C (73°F), 50 mm/min	>50	%	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	15	%	ISO 527-1/-2
Flexural modulus, 23°C (73°F)	483 - 758	MPa	ASTM D790
Tensile modulus, 23°C (73°F)	700	MPa	ASTM D638
Coefficient of friction dynamic vs steel, 23°C (73°F)	0.33		ASTM D1895
Coefficient of friction static vs steel, 23°C (73°F)	0.33		ASTM D1894
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	16 - 19	mg	ASTM G195-13A
속성	값	UNIT	테스트 표준
Glass transition temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Vicat softening temperature, 50N at 50°C/h	76	°C	ISO 306
Limiting oxygen index (LOI)	42	%	ASTM D2863
Coefficient of linear thermal expansion, 23°C (73°F)	126 - 185	10E-6 / °K	ASTM D696
Specific heat temperature, 23°C (73°F)	745 - 958		ISO 11357-1/-2
Heat deflection temperature, 0.45 MPa	68	°C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa	48	°C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa, 138°C/h	40 - 55	°C	ASTM D648
Heat deflection temperature, 0.45 MPa, 138°C/h	60-75	°C	ASTM D648
Thermal conductivity	0.144 - 0.18	W/m-K	ASTM D433
Melting temperature, 10°C/min	143	°C	ISO 11357-1/-3

THERMAL PROPERTIES ELECTRICAL PROPERTIES

속성	값	UNIT	테스트 표준
Dielectric constant, 1kHz	3.5 - 10.6		ASTM D150
Dielectric strength, 23°C (73,4°F)	1.3 - 1.5	kV/mm	ASTM D149
Relative permittivity, 100Hz	11		
Relative permittivity, 1MHz	6		
Relative thermal index	130		
Dissipation factor, 100Hz	570	E-4	
Dissipation factor, 1MHz	2340	E-4	
Dissipation factor	0.02 - 0.21		ASTM D150

KYNAR FLEX® 2800-20

OTHER PROPERTIES

속성	값	UNIT	테스트 표준
Specific gravity, 23°C (73°F)	1.77 - 1.8	g/cm³	
Water absorption, Saturated in water at 23°C (73°F)	0.03	%	ISO 62

포장



Available packaging:

- 25 kg / 55 lb rigid container

특징

- 불과 연기

DIAGRAMS



Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

arkema.com

ARKEMA