

TECHNICAL DATA SHEET

KYNAR FLEX® 2850 PC POWDER

FLUORINATED COPOLYMER POWDER

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® 2850 PC resin powder coating is a semi-crystalline copolymer of vinylidene fluoride and hexafluoropropylene.

It has a special particle size making it ideal for spray applied powder coating on metal substrates for abrasion and corrosion protection

DESIGNATION

PVDF

DELIVERY FORM

• Powder

RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Melt viscosity, 230°C (445°F) at 100 s-1	4 - 8 kPo	ASTM D3835
Melt flow index (MFR), 235°C / 5 kg (455°F / 11 lb)	8 - 25 g/10min	ASTM D1238
Melt volume flow rate (MVR), 230°C / 3.8 kg (445°F / 8.3 lb)	7.5 cm³/10min	ISO 1133

MECHANICAL PROPERTIES

속성	값	테스트 표준
Yield stress, 23°C (73°F)	31 - 41.4 MPa	ASTM D638
Yield strain, 23°C (73°F), 50 mm/min	10 %	ISO 527-1/-2
Stress at break, 23°C (73°F)	27.6 - 48.3 MPa	ASTM D638
Nominal strain at break, 23°C (73°F), 50 mm/min	>50 %	ISO 527-1/-2
Flexural modulus, 23°C (73°F)	1030 - 1240 MPa	ASTM D790
Compression strength, 23°C (73°F)	41.4 - 586 MPa	ASTM D695
Izod impact unnotched strength, 23°C (73°F)	No Break	ASTM D256
Izod impact notched strength, 23°C (73°F)	0.16 - 0.427 J/m	ASTM D256
Hardness, Shore D	70 - 75	ASTM D2240
Tensile modulus, 23°C (73°F)	1275 MPa	ASTM D638
Coefficient of friction dynamic vs steel, 23°C (73°F)	0.19	ASTM D1895
Coefficient of friction static vs steel, 23°C (73°F)	0.26	ASTM D1894
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	6 - 9 mg	ASTM G195-13A

KYNAR FLEX® 2850 PC POWDER

속성	값	테스트 표준
Limiting oxygen index (LOI)	43 %	ASTM D2863
Coefficient of linear thermal expansion, 23°C (73°F)	126 - 185 10E-6 / °K	ASTM D696
Specific heat temperature, 23°C (73°F)	745 - 958	ISO 11357-1/-2
Heat deflection temperature, 1.8 MPa	46 °C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa, 138°C/h	37.8 - 55 °C	ASTM D648
Heat deflection temperature, 0.45 MPa, 138°C/h	60-75 °C	ASTM D648
Glass transition temperature	-40.6 - -38.3 °C	ASTM D7028
Thermal conductivity	0.144 - 0.18 W/m-K	ASTM D433
Melting temperature, 10°C/min	158 °C	ISO 11357-1/-3

THERMAL PROPERTIES/ELECTRICAL PROPERTIES

속성	값	테스트 표준
Dielectric constant, 1kHz	3.5 - 10.2	ASTM D150
Dielectric strength, 23°C (73,4°F)	1.3 - 1.6 kV/mm	ASTM D149
Dissipation factor	0.01 - 0.22	ASTM D150

OTHER PROPERTIES

속성	값	테스트 표준
Specific gravity, 23°C (73°F)	1.77 - 1.8 g/cm ³	
Water absorption, Saturated in water at 23°C (73°F)	0.03 %	ISO 62

SPECIAL CHARACTERISTICS

- Flame & smoke

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA