

TECHNICAL DATA SHEET

KYNAR FLEX[®] 3030-50

FLUORINATED COPOLYMER PELLET

KYNAR FLEX[®] 3030-50 resin is a copolymer of vinylidene fluoride and hexafluoropropylene specifically designed for cable, tubing and heat shrink tubing applications.

- Characteristics:
- Excellent crosslink efficiency
 - Very high flexibility
 - High melting point
 - Excellent low temperature impact resistance

A powder form is also available: KYNAR FLEX[®] 3031-50.

TYPE

PVDF

MAIN APPLICATIONS

- 플레넘 케이블

배송 방식 (문의)

- 파렛트

RHEOLOGICAL PROPERTIES

속성	값	UNIT	테스트 표준
Melt viscosity, 230°C (445°F) at 100 s-1	21 - 30	kPo	ASTM D3835
Melt flow index (MFR), 235°C / 5 kg (455°F / 11 lb)	2.5 - 7.5	g/10min	ASTM D1238

MECHANICAL PROPERTIES

속성	값	UNIT	테스트 표준
Tensile modulus, 23°C (73°F)	276	MPa	ASTM D638
Yield stress, 23°C (73°F)	11.7 - 15.9	MPa	ASTM D638
Yield strain, 23°C (73°F)	25 - 40	%	ASTM D638
Stress at break, 23°C (73°F)	18.6 - 24.1	MPa	ASTM D638
Flexural modulus, 23°C (73°F)	248 - 303	MPa	ASTM D790
Izod impact notched strength, 23°C (73°F)	No Break		ASTM D256
Hardness, Shore D	50 - 60		ASTM D2240
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	28 - 33	mg	ASTM G195-13A

KYNAR FLEX® 3030-50

속성	값	UNIT	테스트 표준
Limiting oxygen index (LOI)	43	%	ASTM D2863
Coefficient of linear thermal expansion, 23°C (73°F)	153 - 194	10E-6 / °K	ASTM D696
Glass transition temperature	-40	°C	ASTM D7028
Melting temperature, 10°C/min	164	°C	ASTM D3418

THERMAL PROPERTIES ELECTRICAL PROPERTIES

속성	값	UNIT	테스트 표준
Surface resistivity, 23°C (73,4°F)	7.6E+11 - 7.9E+11	ohm/sq	ASTM D257
Dielectric strength, 23°C (73,4°F)	1 - 1.2	kV/mm	ASTM D149
Volumic (transversal) resistivity, DC, 20°C (68°F)/50%RH	2.0E+12	ohm*m	ASTM D257

OTHER PROPERTIES

속성	값	UNIT	테스트 표준
Specific gravity, 23°C (73°F)	1.78 - 1.82	g/cm³	
Water absorption, Saturated in water at 23°C (73°F)	0.05	%	ASTM D570

포장 (문의 - 순서 이상)

Available packaging:

- 25 kg / 55 lb rigid container

특징

- 화염 및 연기

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

arkema.com

