

TECHNICAL DATA SHEET

KYNAR FLEX[®] PPA 2201 POWDER

FLUORINATED COPOLYMER POWDER

The use of Kynar Flex[®] PPA 2201 resinat 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control

DESIGNATION

PVDF

MAIN APPLICATIONS

- Polymer Processing Aid

DELIVERY FORM

- Powder

THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	144 °C	ISO 11357-1/-3

OTHER PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Apparent density, 23°C (73°F)	0.7 g/cm ³	Internal Arkema

SPECIAL CHARACTERISTICS

- Flame & smoke

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80