

KYNAR FLEX®

TECHNICAL DATA SHEET

KYNAR FLEX® PPA 2201 POWDER

FLUORINATED COPOLYMER POWDER

The use of Kynar Flex® PPA 2201 resin at 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control

DESIGNATION

PVDF

DELIVERY FORM

- Powder

속성	값	테스트 표준
Melting temperature, 10°C/min	144 °C	ISO 11357-1/-3

OTHER PROPERTIES

속성	값	테스트 표준
Apparent density, 23°C (73°F)	0.7 g/cm ³	Internal Arkema

SPECIAL CHARACTERISTICS

- Flame & smoke

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA