

TECHNICAL DATA SHEET

KYNAR FLEX[®] PPA 5301 POWDER

FLUORINATED COPOLYMER POWDER

KYNAR FLEX[®] resins are fluorinated thermoplastic copolymers.
KYNAR FLEX[®] PPA 5301 resin is specially designed pellet used as a polymer process aid (PPA) for polyolefins.
The use of KYNAR FLEX[®] PPA 5301 resin at 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control.

TYPE	DELIVERY FORM
PVDF	• Powder
MAIN APPLICATIONS	
• Polymer Processing Aid	

THERMAL PROPERTIES

プロパティ	価値	UNIT	テスト基準
Melting temperature, 10°C/min	147	°C	ISO 11357-1/-3

OTHER PROPERTIES

プロパティ	価値	UNIT	テスト基準
Apparent density, 23°C (73°F)	0.77	g/cm³	Internal Arkema

包装

Available packaging:

- 25 kg / 55 lb 袋
- 500 gram / 1 lb jar

SPECIAL CHARACTERISTICS

- Flame & smoke

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80