

## TECHNICAL DATA SHEET

### KYNAR FLEX® PPA 8600

#### FLUORINATED COPOLYMER PELLET

KYNAR FLEX® resins are fluorinated thermoplastic copolymers.

KYNAR FLEX® PPA 8600 resin is specially designed pellet used as a polymer process aid (PPA) for polyolefins.

The use of KYNAR FLEX® PPA 8600 resin at 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control.

This product is also available on a powder form as KYNAR FLEX® PPA 8601 resin.

#### DESIGNATION

PVDF

#### DELIVERY FORM

- Pellets

속성	값	테스트 표준
Glass transition temperature, 10°C/min	-40 °C	ISO 11357-1/-2
Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3

#### SPECIAL CHARACTERISTICS

- Flame & smoke

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790