

## TECHNICAL DATA SHEET KYNAR® 4000 HD

### FLUORINATED HOMOPOLYMER PELLETT

Kynar® resins are fluorinated thermoplastic homopolymers.

Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermo-mechanical properties.

Kynar® 4000 HD resin is a standard grade of granules for injection molding.

#### DESIGNATION

PVDF

#### DELIVERY FORM

- Pellets

### RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Melt flow index (MFR), 230°C / 5 kg (446°F / 11 lb)	14 g/10min	ISO 1133
Melt viscosity, 230°C (445°F) at 100 s-1	13 kPo	ASTM D3835

### MECHANICAL PROPERTIES

속성	값	테스트 표준
Tensile modulus	MPa	ISO 527-1/-2
Yield stress	51 MPa	ISO 527-1/-2
Yield strain	9 %	ISO 527-1/-2
Nominal strain at break	50 %	ISO 527-1/-2
속성	값	테스트 표준
Heat deflection temperature, 1.8 MPa	106 °C	ISO 75-1/-2
Limiting oxygen index (LOI)	80 %	ASTM D2863
Melting temperature, 10°C/min	171 °C	ISO 11357-1/-3

### OTHER PROPERTIES

속성	값	테스트 표준
Specific gravity	1.78 g/cm <sup>3</sup>	ISO 1183-1

### SPECIAL CHARACTERISTICS

- Flame & smoke

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80