

TECHNICAL DATA SHEET

KYNAR® 740 RED

FLUORINATED HOMOPOLYMER PELLET

Kynar® resins are fluorinated thermoplastic homopolymers.

Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermo-mechanical properties.

Kynar® 740 resin is a grade of granules for injection molding, rotomolding applications and multifilament extrusion. This product is NSF/ANSI/CAN 61 certified.

TYPE

PVDF

MAIN APPLICATIONS

• CPI - その他

配送形態

• ペレット

RHEOLOGICAL PROPERTIES

プロパティ	価値	UNIT	テスト基準
Melt viscosity, 230°C (445°F) at 100 s-1	16 - 22	kPo	ASTM D3835
Shrinkage, Normal (t+24h)	2	%	ISO 294-4
Shrinkage, Parallel (t+24h)	2	%	ISO 294-4
Melt flow index (MFR), 235°C / 5 kg (455°F / 11 lb)	1.5 - 3	g/10min	ASTM D1238
Melt volume flow rate (MVR), 230°C / 5 kg (446°F / 11 lb)	1.1	cm³/10min	ISO 1133

MECHANICAL PROPERTIES

プロパティ	価値	UNIT	テスト基準
Yield stress, 23°C (73°F)	44.8 - 55.2	MPa	ASTM D638
Stress at break, 23°C (73°F)	34.5 - 55.2	MPa	ASTM D638
Compression strength, 23°C (73°F)	68.9 - 103	MPa	ASTM D695
Izod impact unnotched strength, 23°C (73°F)	1070-4270	J/m	ASTM D256
Izod impact notched strength, 23°C (73°F)	96-214	J/m	ASTM D256
Charpy unnotched impact strength, 23°C (73°F)	244	kJ/m2	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	186	kJ/m2	ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	14	kJ/m2	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	5	kJ/m2	ISO 179 1eA
Hardness, Shore D	76 - 80		ASTM D2240
Nominal strain at break, 23°C (73°F), 50 mm/min	>50	%	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	7	%	ISO 527-1/-2

KYNAR® 740 RED

プロパティ	価値	UNIT	テスト基準
Flexural modulus, 23°C (73°F)	1380 - 2310	MPa	ASTM D790
Tensile modulus, 23°C (73°F)	1800	MPa	ASTM D638
Coefficient of friction dynamic vs steel, 23°C (73°F)	0.14		ASTM D1895
Coefficient of friction static vs steel, 23°C (73°F)	0.2		ASTM D1894
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	5 - 9	mg	ASTM G195-13A

THERMAL PROPERTIES

プロパティ	価値	UNIT	テスト基準
Glass transition temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Vicat softening temperature, 50N at 50°C/h	135	°C	ISO 306
Limiting oxygen index (LOI)	44	%	ASTM D2863
Yellow card available	yes		
Coefficient of linear thermal expansion, 23°C (73°F)	119 - 144	10E-6 / °K	ASTM D696
Specific heat temperature, 23°C (73°F)	745 - 958		ISO 11357-1/-2
Heat deflection temperature, 0.45 MPa	135	°C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa	105	°C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa, 138°C/h	105 - 115	°C	ASTM D648
Heat deflection temperature, 0.45 MPa, 138°C/h	125-140	°C	ASTM D648
Thermal conductivity	0.17 - 0.19	W/m-K	ASTM D433
Melting temperature, 10°C/min	168	°C	ISO 11357-1/-3

ELECTRICAL PROPERTIES

プロパティ	価値	UNIT	テスト基準
Comparative tracking index	600		IEC 60112
Dielectric constant, 1kHz	4.5 - 9.5		ASTM D150
Relative permittivity, 100Hz	11		IEC 62631-2-1
Relative permittivity, 1MHz	8		IEC 62631-2-1
Relative thermal index	150		
Dissipation factor, 100Hz	260	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	2310	E-4	IEC 62631-2-1
Dissipation factor	0.01 - 0.21		ASTM D150

KYNAR® 740 RED

OTHER PROPERTIES

プロパティ	価値	UNIT	テスト基準
Moisture absorption, At equilibrium at 23°C (73°F) / 50%HR	0.015	%	ISO 62
Water absorption, Saturated in water at 23°C (73°F)	0.03	%	ISO 62
, 23°C (73°F)	1.77 - 1.79	g/cm³	ISO 1183-1

パッケージング

- Available packaging:
- 25 kg / 55 lb 袋
 - 25 kg / 55 lb rigid container
 - 680 kg / 1500 lb big bag

PROCESSING CONDITIONS:

- 典型的な熔融温度 (最小/推奨/最大) - 射出成形:180°C / 210°C / 240°C (355°F / 410°F / 465°F)
- 典型的な金型温度 - 射出成形:20-80°C (70-175°F)

特別な特性

- 炎と煙