

## TECHNICAL DATA SHEET

# KYNAR® ADXFLEX 2250-05

## FLUORINATED COPOLYMER PELLET

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® ADX 2250-05 resin is a semi-crystalline flexible functionalized copolymer designed for co-extrusion with other materials to improve interlayer adhesion. It is particularly suited to tubing, pipe and film co-extrusion applications.

Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermo-mechanical properties.

More over, this grade increases the potential of adhesion on materials as polyamides, polyolefins and can be coextruded.

### DESIGNATION

PVDF

### MAIN APPLICATIONS

- Additives For Adhesives

### DELIVERY FORM

- Pellets

## RHEOLOGICAL PROPERTIES

プロパティ	価値	テスト基準
Melt volume flow rate (MVR), 230°C / 3.8 kg (445°F / 8.3 lb)	6 cm <sup>3</sup> /10min	ISO 1133

## MECHANICAL PROPERTIES

プロパティ	価値	テスト基準
Yield stress, 23°C (73°F), 50 mm/min	12 MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	18 %	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	>50 %	ISO 527-1/-2

## THERMAL PROPERTIES

プロパティ	価値	テスト基準
Melting temperature, 10°C/min	123 °C	ISO 11357-1/-3
Heat deflection temperature, 1.8 MPa	33 °C	ISO 75-1/-2

## ELECTRICAL PROPERTIES

プロパティ	価値	テスト基準
Dielectric strength, 23°C (73,4°F)	13 kV/mm	IEC 60243-1

## OTHER PROPERTIES

プロパティ	価値	テスト基準
Water absorption, Saturated in water at 23°C (73°F)	0.1 %	ISO 62

# KYNAR® ADXFLEX 2250-05

## SPECIAL CHARACTERISTICS

- Flame & smoke

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**