

TECHNICAL DATA SHEET

KYNAR® ADXFLEX 2250-05

FLUORINATED COPOLYMER PELLET

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® ADX 2250-05 resin is a semi-crystalline flexible functionalized copolymer designed for co-extrusion with other materials to improve interlayer adhesion. It is particularly suited to tubing, pipe and film co-extrusion applications.

Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermo-mechanical properties.

More over, this grade increases the potential of adhesion on materials as polyamides, polyolefins and can be coextruded.

DESIGNATION

PVDF

DELIVERY FORM

- Pellets

RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Melt volume flow rate (MVR), 230°C / 3.8 kg (445°F / 8.3 lb)	6 cm ³ /10min	ISO 1133

MECHANICAL PROPERTIES

속성	값	테스트 표준
Yield stress, 23°C (73°F), 50 mm/min	12 MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	18 %	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	>50 %	ISO 527-1/-2
속성	값	테스트 표준
Melting temperature, 10°C/min	123 °C	ISO 11357-1/-3
Heat deflection temperature, 1.8 MPa	33 °C	ISO 75-1/-2

THERMAL PROPERTIES ELECTRICAL PROPERTIES

속성	값	테스트 표준
Dielectric strength, 23°C (73,4°F)	13 kV/mm	IEC 60243-1

OTHER PROPERTIES

속성	값	테스트 표준
Water absorption, Saturated in water at 23°C (73°F)	0.1 %	ISO 62

SPECIAL CHARACTERISTICS

- Flame & smoke

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80