

TECHNICAL DATA SHEET

KYNAR® MG15 POWDER

FLUORINATED HOMOPOLYMER POWDER

KYNAR® resins are fluorinated thermoplastic homopolymers.

KYNAR® MG15 resin is a crystalline high viscosity polymer of polyvinylidene difluoride. It is an engineering polymer with an outstanding balance of physical strength and high chemical resistance which make it ideal for micro and ultra-filtration membranes for durable water purification and other applications.

KYNAR® MG15 resin is soluble in selected solvents and can be used in solution processing applications. It is especially recommended for hollow fiber and flat sheet membranes.

KYNAR® MG15 resin has NSF, FDA, and USP Class VI certifications for use in potable water, food processing, and bio-pharma applications.

DESIGNATION

PVDF

MAIN APPLICATIONS

- Water Membrane

DELIVERY FORM

- Powder

RHEOLOGICAL PROPERTIES

プロパティ	価値	テスト基準
Melt viscosity, 230°C (445°F) at 100 s-1	33 - 39 kPo	ASTM D3835

MECHANICAL PROPERTIES

プロパティ	価値	テスト基準
Tensile modulus, 23°C (73°F)	1845 MPa	ASTM D638
Yield stress, 23°C (73°F)	44.8 - 55.2 MPa	ASTM D638
Flexural modulus, 23°C (73°F)	1380 - 2310 MPa	ASTM D790

THERMAL PROPERTIES

プロパティ	価値	テスト基準
Glass transition temperature, 10°C/min	-40 °C	ISO 11357-1/-2
Melting temperature, 10°C/min	168 °C	ISO 11357-1/-3

OTHER PROPERTIES

プロパティ	価値	テスト基準
Specific gravity, 23°C (73°F)	1.77 - 1.79 g/cm³	
Solution viscosity, 20°C (68°F)	1500 cPo	Internal Arkema
Water absorption, Saturated in water at 23°C (73°F)	0.04 %	ASTM D570

KYNAR® MG15 POWDER

SPECIAL CHARACTERISTICS

- Flame & smoke

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA