

## TECHNICAL DATA SHEET ORGALLOY® RDG 113

### POLYAMIDE ALLOY PELLET

ORGALLOY® RDG 113 is a polyamide alloy. This natural flexible grade is designed for extrusion to produce refrigerant barrier layer in automotive & non automotive air conditioning rubber hose.

#### DESIGNATION

PA\*

#### DELIVERY FORM

- Pellets

#### TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

#### ADDITIVES

- Heat Stabilized
- Light Stabilized

### MECHANICAL PROPERTIES

속성	DRY / COND VALUE*	테스트 표준
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50 %	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 4.4 %	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 47 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	2253 / 2253 MPa	ISO 527-1/-2

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

속성	값	테스트 표준
Melting temperature, 10°C/min	229 °C	ISO 11357-1/-3

### OTHER PROPERTIES

속성	값	테스트 표준
Specific gravity, 23°C (73°F)	1.12 g/cm <sup>3</sup>	ISO 1183-1

### PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 21 kg / 44 lb bags

# ORGALLOY® RDG 113

## SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 250°C / 270°C / 290°C (480°F / 520°F / 555°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**