

## TECHNICAL DATA SHEET

# ORGASOL® 2002 ES 5 NAT 3

## ULTRAFINE POLYAMIDE POWDER

ORGASOL® 2002 ES5 NAT 3 is spheroidal polyamide 12 powder with a narrow particle size distribution and an average diameter of 50µm. ORGASOL® 2002 ES5 NAT 3 has a melting temperature of 177°C. An extremely high level of quality is achieved through rigorous control of the particle size distribution & porosity, ensuring excellent consistency of performance.

ORGASOL® is a range of high performance ultra-fine polyamide powders used as multifunctional additives in coatings, inks, varnishes and technical compounds.

The introduction of ORGASOL® polyamide powders in formulations is easy thanks to their good dispersion capacity, their reduced impact on rheology and their low density.

ORGASOL® polyamide powders are surface modifiers, specifically designed for gloss control, texture creation and haptic properties adjustment. They also improve blocking resistance and reduce coefficient of friction.

Abrasion, scratch, impact resistances and flexibility of coatings, inks and varnishes and technical compounds can be significantly improved using ORGASOL® polyamide powders.

### DESIGNATION

PA12

### MAIN APPLICATIONS

- Coatings

### DELIVERY FORM

- Powder

### TRANSFORMATION PROCESSES

- Formulation ingredients

## THERMAL PROPERTIES

プロパティ	価値	テスト基準
Melting temperature, 10°C/min	177 °C	ISO 11357-1/-3

## OTHER PROPERTIES

プロパティ	価値	テスト基準
Apparent density, Non compacted	0.43	ISO 1068
Specific surface area (SSA)	1 m <sup>2</sup> /g	ISO 9277
Fine particles (D10)	41 µm	ISO 13319
Median particles (D50)	50 µm	ISO 13319
Coarse particles (D90)	58 µm	ISO 13319

## 包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 20 kg / 44 lb bags

## 賞味期限

Three years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

Headquarter: Arkema France  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80