

TECHNICAL DATA SHEET

PEBAX® 2533 SD 02

POLYETHER BLOCK AMIDE PELLET

PEBAX® 2533 SD 02 is a polyether block amide, a thermoplastic elastomer made of flexible polyether and rigid polyamide. This SD grade is heat & UV stabilized and contains mold release additive. It is used in sport and consumer applications.

DESIGNATION

PEBA

MAIN APPLICATIONS

- Flavour And Fragrance

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Film Extrusion
- Injection Molding
- Tube Extrusion

ADDITIVES

- Release agent

RHEOLOGICAL PROPERTIES

プロパティ	価値	テスト基準
Shrinkage, Parallel (t+24h)	0.6 %	ISO 294-4
Shrinkage, Normal (t+24h)	0.7 %	ISO 294-4

MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Compression set	19 / - %	ISO 815
Hardness, Shore A, 15 s	- / 74	ISO 868
Hardness, Shore D, 15 s	- / 22	ISO 868
Charpy unnotched impact strength, 23°C (73°F)	No Break / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	No Break / No Break	ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	No Break / No Break	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	No Break / No Break	ISO 179 1eA
Stress at 50% strain, 23°C (73°F), 50 mm/min	3 / 3 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	12 / 10 MPa	ISO 527-1/-2
Abrasion resistance	130 / - mm ³	ISO 4649
Flexural modulus, 23°C (73°F)	- / 12 MPa	ISO 178

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

PEBAX® 2533 SD 02

THERMAL PROPERTIES

プロパティ	価値	テスト基準
Glass transition temperature, 10°C/min	-65 °C	ISO 11357-1/-2
Heat deflection temperature, 0.45 MPa	42 °C	ISO 75-1/-2
Melting temperature, 10°C/min	134 °C	ISO 11357-1/-3

ELECTRICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Surface resistivity, 23°C (73,4°F)	- / 3.0E+12 ohm/sq	IEC 62631-3-2
Volumic (transversal) resistivity, 23°C (73,4°F)	- / 1.3E+10 ohm/m	IEC 62631-3-1
Comparative tracking index, 23°C (73,4°F)	- / 600	IEC 60112
Dielectric stress, 23°C (73,4°F)	- / 36	IEC 60243-1
Relative permittivity, 100Hz	- / 6	IEC 60250
Relative permittivity, 1Mhz	- / 6	IEC 60250
Dissipation factor, 100Hz	- / 552	IEC 60250
Dissipation factor, 1Mhz	- / 552	IEC 60250

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

OTHER PROPERTIES

プロパティ	価値	テスト基準
Moisture absorption, At equilibrium at 23°C (73°F) / 50%HR	0.4 %	ISO 62
Water absorption, 23°C(73°F), immersion, equilibrium	1.2 %	ISO 62
Specific gravity, 23°C (73°F)	1 g/cm ³	ISO 1183-1

包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:





- 典型的な溶融温度 (最小 / 推奨 / 最大) - 射出成形: 180°C / 210°C / 240°C (355°F / 410°F / 465°F)
- 典型的な金型温度 - 射出成形: 10-30°C (50-90°F)
- Drying time and temperature: 55-65°C (130-150°F) / 4-8 hours

REGIONAL AVAILABILITY

Asia Pacific, Europe, Latin America and the Caribbean, Middle East, Northern America

PEBAX® 2533 SD 02

DIAGRAMS



Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790