

TECHNICAL DATA SHEET

PEBAX® 4533 SA 01 MED

POLYETHER BLOCK AMIDE PELLET

PEBAX® 4533 SA 01 MED is a polyether block amide, a thermoplastic elastomer made of flexible polyether and rigid polyamide. This grade offers the highest quality and is approved in medical applications. Upon request, letters regarding USP Class VI compliance can be provided.

DESIGNATION

PEBA

MAIN APPLICATIONS

- Health - Consumable - Others
- Health - Consumable - Catheters
- Other Medical

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Film Extrusion
- Injection Molding
- Tube Extrusion

RHEOLOGICAL PROPERTIES

プロパティ	価値	テスト基準
Shrinkage, Parallel (t+24h)	0.6 %	ISO 294-4
Shrinkage, Normal (t+24h)	1.1 %	ISO 294-4

MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Hardness, Shore A, 15 s	- / 90	ISO 868
Hardness, Shore D, 15 s	- / 41	ISO 868
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	No Break / No Break	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	No Break / No Break	ISO 179 1eA
Stress at 50% strain, 23°C (73°F), 50 mm/min	9 / 9 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	88 / 81 MPa	ISO 527-1/-2
Flexural modulus, 23°C (73°F)	- / 86 MPa	ISO 178
Stress at break, 23°C (73°F), 50 mm/min	- / 42 MPa	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	> 550 / > 550 %	ISO 527-1/-2

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

PEBAX® 4533 SA 01 MED

THERMAL PROPERTIES

プロパティ	価値	テスト基準
Melting temperature, 10°C/min	147 °C	ISO 11357-1/-3

OTHER PROPERTIES

プロパティ	価値	テスト基準
Moisture absorption, At equilibrium at 23°C (73°F) / 50%HR	0.4 %	ISO 62
Water absorption, 23°C(73°F), immersion, equilibrium	1.2 %	ISO 62
Specific gravity, 23°C (73°F)	1.01 g/cm ³	ISO 1183-1

包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- 典型的な溶融温度 (最小 / 推奨 / 最大) - 射出成形: 210°C / 240°C / 270°C (410°F / 430°F / 520°F)
- 典型的な金型温度 - 射出成形: 10-30°C (50-90°F)
- Drying time and temperature: 60-70°C (140-160°F) / 4-8 hours

REGIONAL AVAILABILITY

Africa, Asia Pacific, Europe, Latin America and the Caribbean, Middle East, Northern America

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA