

## TECHNICAL DATA SHEET PEBAX® 5513 SA 01

### POLYETHER BLOCK AMIDE PELLET

PEBAX® 5513 SA 01 is a polyether block amide, a thermoplastic elastomer made of flexible polyether and rigid polyamide. This SA grade offers the highest quality. It is used in sport and consumer applications, especially when food contact compliance is requested. Added to PA6, PEBAX® 5513 SA 01 enhances the properties of PA6, especially at low temperatures and low humidity content, while maintaining the transparency of the polyamide film and improving its soft touch.

#### DESIGNATION

PEBA

#### MAIN APPLICATIONS

- Industry - Others
- Industry - Distribution
- Additives PA6

#### DELIVERY FORM

- Pellets

#### TRANSFORMATION PROCESSES

- Extrusion - General
- Film Extrusion
- Injection Molding
- Tube Extrusion

### RHEOLOGICAL PROPERTIES

プロパティ	価値	テスト基準
Shrinkage, Parallel (t+24h)	0.7 %	ISO 294-4
Shrinkage, Normal (t+24h)	0.8 %	ISO 294-4

### MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Hardness, Shore D, 15 s	- / 54	ISO 868
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	>500 / > 500 %	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	32 / 30 %	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	14 / 13 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	- / 180 MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	No Break / No Break	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 34 kJ/m2	ISO 179 1eA
Stress at break, 23°C (73°F), 50 mm/min	- / 60 MPa	ISO 527-1/-2

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

# PEBAX® 5513 SA 01

## THERMAL PROPERTIES

プロパティ	価値	テスト基準
Vicat softening temperature, 50N at 50°C/h	169 °C	ISO 306
Melting temperature, 10°C/min	195 °C	ISO 11357-1/-3

## OTHER PROPERTIES

プロパティ	価値	テスト基準
Moisture absorption, At equilibrium at 23°C (73°F) / 50%HR	1.3 %	ISO 62
Water absorption, 23°C(73°F), immersion, equilibrium	6.7 %	ISO 62
Specific gravity, 23°C (73°F)	1.09 g/cm <sup>3</sup>	ISO 1183-1

## 包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 454 kg / 1000 lb rigid containers

## 賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## PROCESSING CONDITIONS:

- 典型的な熔融温度 (最小 / 推奨 / 最大) - 射出成形: 210°C / 240°C / 270°C (410°F / 430°F / 520°F)
- 典型的な金型温度 - 射出成形: 20-60°C (70-140°F)
- Drying time and temperature: 65-75°C (150-165°F) / 4-6 hours

## REGIONAL AVAILABILITY

Asia Pacific, Europe, Latin America and the Caribbean, Middle East, Northern America

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**