

TECHNICAL DATA SHEET

PEBAX[®] 7233 SA 01 MED

POLYETHER BLOCK AMIDE PELLET

PEBAX[®] 7233 SA 01 MED is a polyether block amide, a thermoplastic elastomer made of flexible polyether and rigid polyamide. This grade offers the highest quality and is approved in medical applications. Upon request, letters regarding USP Class VI compliance can be provided.

DESIGNATION

PEBA

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Film Extrusion
- Injection Molding
- Tube Extrusion

RHEOLOGICAL PROPERTIES

속성	값	UNIT	테스트 표준
Shrinkage, Parallel (t+24h)	0.8	%	ISO 294-4
Shrinkage, Normal (t+24h)	0.9	%	ISO 294-4

MECHANICAL PROPERTIES

속성	DRY / COND VALUE*	UNIT	테스트 표준
Hardness, Shore D, 15 s	- / 61		ISO 868
Charpy unnotched impact strength, 23°C (73°F)	- / No Break		ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break		ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	> 300 / > 300	%	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 18	%	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 26	MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	- / 510	MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 15	kJ/m2	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 10	kJ/m2	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 513	MPa	ISO 178
Stress at break, 23°C (73°F), 50 mm/min	- / 56	MPa	ISO 527-1/-2

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

PEBAX® 7233 SA 01 MED

속성	값	UNIT	테스트 표준
Vicat softening temperature, 50N at 50°C/h	106	°C	ISO 306
Melting temperature, 10°C/min	174	°C	ISO 11357-1/-3

OTHER PROPERTIES

속성	값	UNIT	테스트 표준
Moisture absorption, At equilibrium at 23°C (73°F) / 50%HR	0.7	%	ISO 62
Water absorption, 23°C (73°F), immersion, equilibrium	0.9	%	ISO 62
Specific gravity, 23°C (73°F)	1.01	g/cm³	ISO 1183-1

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 20 kg / 44 lb 가방

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 230°C / 260°C / 290°C (445°F / 500°F / 555°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 70-80°C (160-175°F) / 4-6 hours

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80