

TECHNICAL DATA SHEET

PEBAX[®] CLEAR 800

POLYETHER BLOCK AMIDE PELLET

PEBAX[®] Clear 800 combines transparency, toughness and stiffness with the unique performance of Pebax[®] thermoplastic elastomer

DESIGNATION

PEBA

MAIN APPLICATIONS

- Footwear - Outsole/Components
- Frames
- Accessories

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Injection Molding

RHEOLOGICAL PROPERTIES

プロパティ	価値	テスト基準
Shrinkage, Parallel (t+24h) (2mm thick plate, mold at 40°C)	0.7 %	ISO 294-4
Shrinkage, Normal (t+24h) (2mm thick plate, mold at 40°C)	0.7 %	ISO 294-4

MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Flexural modulus, 23°C (73°F)	- / 850 MPa	ISO 178
Tensile modulus, 23°C (73°F), 1 mm/min	- / 900 MPa	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 29 MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 6 %	ISO 527-1/-2
Stress at break, 23°C (73°F), 50 mm/min	- / 38 MPa	ISO 527-1/-2
Strain at break, 23°C (73°F), 50 mm/min	- / > 200 %	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 40 kJ/m ²	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 22 kJ/m ²	ISO 179 1eA
Charpy unnotched impact strength, 23°C (73°F)	/ No Break kJ/m ²	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	/ No Break kJ/m ²	ISO 179 1eU
Hardness, Shore D, Instantaneous	/ 75	ISO 868
Hardness, Shore D, 15 s	- / 69	ISO 868

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

PEBAX® CLEAR 800

THERMAL PROPERTIES

プロパティ	価値	テスト基準
Melting temperature, 10°C/min	188 °C	ISO 11357-1/-3

OTHER PROPERTIES

プロパティ	価値	テスト基準
Bio-based carbon content	59 %	ASTM D6866
Transmittance (2mm thick plate)	80 %	ISO 13468-1/-2

包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- 典型的な溶融温度 (最小 / 推奨 / 最大) - 射出成形: 270°C / 285°C / 300°C (520°F / 545°F / 570°F)
- 典型的な金型温度 - 射出成形: 40-80°C (105-175°F)
- Drying time and temperature: 60-70°C (140-160°F) / 4-8 hours

SPECIAL CHARACTERISTICS

- Transparent

REGIONAL AVAILABILITY

Asia Pacific, Europe, Latin America and the Caribbean, Middle East, Northern America

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA