

TECHNICAL DATA SHEET PEBAX® MV 2080

POLYETHER BLOCK AMIDE PELLET

PEBAX® MV 2080 resin is a polyether block amide, a thermoplastic elastomer made of flexible polyether and rigid polyamide. PEBAX® MV 2080 resin is an inherently dissipative polymer and can be dry blended or compounded with an isolative polymer to lower the surface resistivity of the final part.

DESIGNATION

PEBA

MAIN APPLICATIONS

- Film
- Antistatics

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Injection Molding

RHEOLOGICAL PROPERTIES

プロパティ	価値	テスト基準
Shrinkage, Parallel (t+24h)	0.7 %	ISO 294-4
Shrinkage, Normal (t+24h)	1.0 %	ISO 294-4

MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Hardness, Shore D, 15 s	- / 39	ISO 868
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Stress at 50% strain, 23°C (73°F), 50 mm/min	- / 9 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	- / 80 MPa	ISO 527-1/-2
Flexural modulus, 23°C (73°F)	- / 80 MPa	ISO 178

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

THERMAL PROPERTIES

プロパティ	価値	テスト基準
Melting temperature, 10°C/min	160 °C	ISO 11357-1/-3

PEBAX® MV 2080

ELECTRICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Surface resistivity, 23°C (73,4°F)	- / 1.0E+7 ohm/sq	IEC 62631-3-2
Volumic (transversal) resistivity, 23°C (73,4°F)	- / 1.0E+7 ohm/m	IEC 62631-3-1

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

OTHER PROPERTIES

プロパティ	価値	テスト基準
Moisture absorption, At equilibrium at 23°C (73°F) / 50%HR	1.4 %	ISO 62
Water absorption, 23°C(73°F), immersion, equilibrium	48 %	ISO 62
Specific gravity, 23°C (73°F)	1.07 g/cm ³	ISO 1183-1

包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- 典型的な溶融温度 (最小 / 推奨 / 最大) - 射出成形: 210°C / 240°C / 270°C (410°F / 430°F / 520°F)
- 典型的な成型温度 - 射出成形: 10-30°C (50-90°F)
- Drying time and temperature: 60-70°C (140-160°F) / 4-8 hours

SPECIAL CHARACTERISTICS

- Anti-static

REGIONAL AVAILABILITY

Asia Pacific, Europe, Latin America and the Caribbean, Middle East, Northern America

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA