

# TECHNICAL DATA SHEET PLATAMID® H 2513 PELLET

## **COPOLYAMIDE PELLET**

PLATAMID H 2513 PELLET is a thermoplastic copolyamide hot melt adhesive. This low to medium melt viscosity, fast re-crystallizing grade is particularly suitable for manufacturing of of webs, nets, mono- and multi-filaments, and films by extrusion. It has good adhesion to all kinds of textile substrates based on native and synthetic fibers.

This product is available dried with optical brightener (H 2513 TA).

**DESIGNATION** 

PA\*

**DELIVERY FORM** 

Pellets

#### RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Melt volume flow rate (MVR), 160°C / 2.16kg (320°F / 4.4 lb)	26 cm <sup>3</sup> /10min	ISO 1133
속성	값	테스트 표준
Melting temperature, 10°C/min	128 °C	ISO 11357-1/-3

#### OTHER PROPERTIES

속성	값	테스트 표준
Specific gravity, 23°C (73°F)	1.07 g/cm³	ISO 1183-1

#### **PACKAGING**

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 26 kg / 55 lb bags
- 501 kg big bag

### SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

**Headquarter: Arkema France** 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

