PLATAMID[®]

TECHNICAL DATA SHEET

PLATAMID® H 2513 POWDER

COPOLYAMIDE POWDER

PLATAMID H 2513 POWDER is a thermoplastic copolyamide hot melt adhesive. This medium melt viscosity grade is used for the production of fusible interlinings. It offers an excellent laundry resistance up to 60°C and an excellent resistance to all kind of steam treatment.

- This product is available in different grain sizes:
 - PA 80 (0-80 ?m paste dot)
 - PTA 170/20 (0-170 ?m powder dot)
 PTA 170 (80-170 ?m double dot)

DESIGNATION PA*	DELIVERY FORM • Powder
• Adhesives - Apparel/Interlining	TRANSFORMATION PROCESSESScattering, paste, double dot

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melt volume flow rate (MVR), 160°C / 2.16kg (320°F / 4.4 lb)	30 cm³/10min	ISO 1133

THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	128 °C	ISO 11357-1/-3

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 20 kg / 44 lb bags
- 500 kg big bag

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

HPP - 2025-02-17 - Page: 1 / 1

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

ARKEMA

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof. Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

arkema.com