# **PLATAMID**<sup>®</sup>

# TECHNICAL DATA SHEET PLATAMID<sup>®</sup> H 2707 PELLET

### COPOLYAMIDE PELLET

PLATAMID<sup>®</sup> H 2707 PELLET is a thermoplastic copolyamide hot melt adhesive. It is partially manufactured from a renewable and sustainable source (castor oil). This medium to high melt viscosity grade is particularly suitable for manufacturing of of of webs, mono- and multi-filaments, and films by extrusion. It offers a good adhesion at low fusing conditions to various polar substrates (thermoplastics, thermosets, metal, natural fibers, etc.).

This grade is available dried (H 2707 T).

DESIGNATION	DELIVERY FORM
PA*	• Pellets
	TRANSFORMATION PROCESSES
	Melt Spinning

# RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Melt volume flow rate (MVR), 160°C / 2.16kg (320°F / 4.4 lb)	2 cm <sup>3</sup> /10min	ISO 1133
속성	값	테스트 표준
Melting temperature, 10°C/min	102 °C	ISO 11357-1/-3

#### **OTHER PROPERTIES**

속성	값	테스트 표준
Bio-based carbon content, Measured	20 %	ASTM D6866
Specific gravity, 23°C (73°F)	1.06 g/cm <sup>3</sup>	ISO 1183-1

#### PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

26 kg / 55 lb bags

#### SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## SPECIAL CHARACTERISTICS

Bio-based

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

ARKEMA

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on

https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof.

part hereof. Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

arkema.com