# **PLATAMID**<sup>®</sup>

## TECHNICAL DATA SHEET PLATAMID<sup>®</sup> HX 2632 PELLET

#### COPOLYAMIDE PELLET

PLATAMID<sup>®</sup> HX 2632 PELLET is a thermoplastic copolyamide hot melt adhesive. This very low melt viscosity grade is particularly suitable for manufacturing of of of webs, nets, mono- and multi-filaments by extrusion and then converted into very high viscous product providing additional properties as the bonding temperature resistance. A controlled activation of crosslinking reactions can be achieved during a processing step by various means such as peroxides, UV and e-beams. It offers a very good adhesion at low fusing conditions to various kind of polar substrates (thermoplastics, thermosets, metal, natural fibers, etc.).

This product is available undried with optical brightener (HX 2632 FA).

DESIGNATION PA*	DELIVERY FORM • Pellets
	TRANSFORMATION PROCESSES
	<ul><li>Filament extrusion</li><li>Melt Spinning</li></ul>

#### RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Melt volume flow rate (MVR), 160°C / 2.16kg (320°F / 4.4 lb)	70 cm <sup>3</sup> /10min	ISO 1133
속성	값	테스트 표준
Melting temperature, 10°C/min	117 °C	ISO 11357-1/-3

#### PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

26 kg / 55 lb bags

501 kg big bag

### SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80



Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof. Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

#### arkema.com