

# TECHNICAL DATA SHEET PLATAMID® M 1186 PELLET

# **COPOLYAMIDE PELLET**

PLATAMID® M 1186 PELLET is a thermoplastic copolyamide hot melt adhesive. This very low melt viscosity, fast re-crystallizing grade is particularly suitable for spraying, manufacturing of of webs, nets, mono- and multi-filaments, and films by extrusion. It offers a very good adhesion to various polar substrates (thermoplastics, thermosets, metal, natural fibers, etc) and is resistant against steam sterilization. This product is available:

- dried (M 1186 TA)
- undried (M 1186 FA)

#### **DESIGNATION**

**ΡΔ**\*

#### MAIN APPLICATIONS

· Adhesives - Automotive Interior

## **DELIVERY FORM**

Pellets

#### TRANSFORMATION PROCESSES

- · Filament extrusion
- Melt Spinning

## RHEOLOGICAL PROPERTIES

プロパティ	価値	テスト基準
Melt volume flow rate (MVR), 230°C / 2.16 kg (445°F / 4.7 lb)	19 cm³/10min	ISO 1133

#### THERMAL PROPERTIES

プロバティ	価値	テスト基準
Melting temperature, 10°C/min	145 °C	ISO 11357-1/-3

# 包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

25 kg / 55 lb bags

## 賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

**Headquarter: Arkema France** 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

