PLATAMID[®]

TECHNICAL DATA SHEET PLATAMID[®] M 1276 PELLET

COPOLYAMIDE PELLET

PLATAMID[®] M 1276 PELLET is a thermoplastic copolyamide hot melt adhesive. It is partially manufactured from a renewable and sustainable source (castor oil). This medium melt viscosity, fast re-crystallizing grade is particularly suitable for manufacturing of of webs, nets, mono- and multi-filaments, and films by extrusion. It exhibits strong adhesion onto:

- rigid and plasticized PVC as well as ABS, epoxy resin, PU, etc.

- various polar substrates (thermoplastics, thermosets, metal, natural fibers, etc.)

Dense layers of PLATAMID® M 1276 PELLET are known to have barrier properties against PVC plasticizer migration.

This product is available:

- dried (M 1276 TE)
- undried (M 1276 F)

DESIGNATION PA*	DELIVERY FORM • Pellets
	TRANSFORMATION PROCESSES Filament extrusion Melt Spinning

RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Melt volume flow rate (MVR), 160°C / 2.16kg (320°F / 4.4 lb)	6 cm ³ /10min	ISO 1133
속성	값	테스트 표준
Melting temperature, 10°C/min	110 °C	ISO 11357-1/-3

OTHER PROPERTIES

속성	값	테스트 표준
Bio-based carbon content, Measured	26 %	ASTM D6866
Specific gravity, 23°C (73°F)	1.1 g/cm ³	ISO 1183-1

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 26 kg / 55 lb bags
- 501 kg big bag

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

SPECIAL CHARACTERISTICS

- Bio-based
- Versatile adhesion

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80



Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on

https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a nart hereof

part hereof. Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790