

## TECHNICAL DATA SHEET

# PLATAMID<sup>®</sup> M 1422 PELLET

## COPOLYAMIDE PELLET

PLATAMID<sup>®</sup> M 1422 PELLET is a thermoplastic copolyamide hot melt adhesive. This semi-crystallized grade is used in solvent based processes. It has been developed for use in the wire coating industry.

This product is available:

- undried (M 1422 F)
- undried (M 1422/1 F)

### DESIGNATION

PA\*

### DELIVERY FORM

- Pellets

## RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Melt volume flow rate (MVR), 230°C / 2.16 kg (445°F / 4.7 lb)	30 cm <sup>3</sup> /10min	ISO 1133
속성	값	테스트 표준
Melting temperature, 10°C/min	120 °C	ISO 11357-1/-3

## PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 26 kg / 55 lb bags

## SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80