

TECHNICAL DATA SHEET

PLATAMID® M 1657 PELLETT

COPOLYAMIDE PELLETT

PLATAMID® M 1657 PELLETT is a thermoplastic copolyamide hot melt adhesive. This very low melt viscosity, fast re-crystallizing grade is particularly suitable for spraying, manufacturing of webs, nets, mono- and multi-filaments, and films by extrusion. It offers a very good adhesion to various polar substrates (thermoplastics, thermosets, metal, natural fibers, etc) and has a very good dry-cleaning resistance and washing resistance up to 40°C.

This product is available:

- dried with optical brightener (M 1657 TA)
- undried with optical brightener (M 1657 FA)

DESIGNATION

PA*

MAIN APPLICATIONS

- Adhesives - Others

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Filament extrusion
- Melt Spinning

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melt volume flow rate (MVR), 160°C / 2.16kg (320°F / 4.4 lb)	200 cm ³ /10min	ISO 1133

THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	107 °C	ISO 11357-1/-3

OTHER PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Specific gravity, 23°C (73°F)	1.07 g/cm ³	ISO 1183-1

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags
- 500 kg big bag

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790