

TECHNICAL DATA SHEET

PLATAMID® M 1943 PELLET

COPOLYAMIDE PELLET

PLATAMID® M 1943 PELLET is a thermoplastic copolyamide hot melt adhesive. This medium melt viscosity, fast re-crystallizing grade is particularly suitable for spraying, manufacturing of webs, nets, mono- and multi-filaments, and films by extrusion. It offers a very good adhesion to various polar substrates (thermoplastics, thermosets, metal, natural fibers, etc).

This product is available dried with optical brightener (M 1943 TA).

DESIGNATION

PA*

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Filament extrusion
- Melt Spinning

RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Melt volume flow rate (MVR), 160°C / 2.16kg (320°F / 4.4 lb)	10 cm ³ /10min	ISO 1133
속성	값	테스트 표준
Melting temperature, 10°C/min	122 °C	ISO 11357-1/-3

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 26 kg / 55 lb bags

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80