

TECHNICAL DATA SHEET

PRIMGREEN® LAT 12035

METAL COATING PRIMER

PRIMGREEN® LAT 12035 is a water-based, ready-to-use primer recommended in association with RILSAN FINE POWDER® coating to ensure long-lasting performance in corrosive environments. PRIMGREEN® LAT 12035 is one of the undercoats recommended by Arkema, tested and confirmed by customers to ensure a top-quality coating.

MAIN APPLICATIONS

- Water Fluid Coating - Water Accessories
- Water Fluid Coating - Piping Systems
- Powder Coating - Printing Roller Coating
- Powder Coating - Wire Goods
- Powder Coating - Others
- Automotive/Truck - Shaft Coating

DELIVERY FORM

- Liquid

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditioned.

TECHNICAL DATA

PROPERTIES	VALUE	UNIT	STANDARD
Dry residue, After solvent evaporation, 3h at 155°C / 311°F	22 - 23	%	
Flash point	51	°C	DIN 53213
Viscosity, 25°C (77°F)	20 - 45	second	AFNOR n°4
Recommended Dry Film Thickness, Pneumatic gun	8 - 12	µm	
Drying time, 20°C (68°F)	10 - 15	minute	

SHELF LIFE

12 months (according to MSDS storage recommendations)

HEALTH AND SAFETY

- See Safety Data Sheet for Health & Safety Considerations

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux - France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)