

TECHNICAL DATA SHEET

RILSAMID® AECV BLACK P40 T8L

POLYAMIDE 12 PELLET

RILSAMID® AECV BLACK P40 T8L resin is a black colored polyamide 12 compound. This plasticized grade is designed for cable coating.

Designation : ISO 16396 - PA12-P, KG1HL, C14-004

DESIGNATION

PA12-P

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General

ADDITIVES

- Heat Stabilized
- Light Stabilized

RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Melt volume flow rate (MVR), 235°C / 2.16 kg (455°F / 4.4 lb)	23 cm ³ /10min	ISO 1133

MECHANICAL PROPERTIES

속성	DRY / COND VALUE*	테스트 표준
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50 %	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 27 %	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 26 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	- / 420 MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 7 kJ/m ²	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 5 kJ/m ²	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 420 MPa	ISO 178

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

속성	값	테스트 표준
Melting temperature, 10°C/min	172 °C	ISO 11357-1/-3

RILSAMID® AECV BLACK P40 T8L

OTHER PROPERTIES

속성	값	테스트 표준
Specific gravity, 23°C (73°F)	1.01 g/cm ³	ISO 1183-1

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 26 kg / 55 lb bags

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA