

## TECHNICAL DATA SHEET

# RILSAMID® AECV BLACK T8L

## POLYAMIDE 12 PELLET

RILSAMID® AECV BLACK T8L resin is a black colored polyamide 12 compound. This grade is designed for cable coating.

Designation : ISO 16396 - PA12, KG1HL, C16-010

### DESIGNATION

PA12

### MAIN APPLICATIONS

- LT Performance Wire - Growth
- Cables Antitermites
- Cable

### DELIVERY FORM

- Pellets

### TRANSFORMATION PROCESSES

- Sheet Extrusion

### ADDITIVES

- Heat Stabilized
- Light Stabilized

## RHEOLOGICAL PROPERTIES

プロパティ	価値	テスト基準
Melt volume flow rate (MVR), 235°C / 2.16 kg (455°F / 4.4 lb)	12 cm <sup>3</sup> /10min	ISO 1133

## MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	> 50 / > 50 %	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	5 / 10 %	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	41 / 37 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	1350 / 1100 MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 8 kJ/m <sup>2</sup>	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 6 kJ/m <sup>2</sup>	ISO 179 1eA

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

# RILSAMID® AECV BLACK T8L

## THERMAL PROPERTIES

プロパティ	価値	テスト基準
Vicat softening temperature, 50N at 50°C/h	138 °C	ISO 306
Heat deflection temperature, 0.45 MPa	135 °C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa	55 °C	ISO 75-1/-2
Melting temperature, 10°C/min	178 °C	ISO 11357-1/-3

## ELECTRICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Surface resistivity, 23°C (73,4°F)	- / 1.0E+11 ohm/sq	IEC 62631-3-2
Volumic (transversal) resistivity, 23°C (73,4°F)	- / 2.0E+6 ohm/m	IEC 62631-3-1
Comparative tracking index, 23°C (73,4°F)	- / 600	IEC 60112
Dielectric stress, 23°C (73,4°F)	- / 40	IEC 60243-1
Relative permittivity, 100Hz	- / 4	IEC 60250
Relative permittivity, 1Mhz	- / 3	IEC 60250
Dissipation factor, 100Hz	- / 431	IEC 60250
Dissipation factor, 1Mhz	- / 431	IEC 60250

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

## OTHER PROPERTIES

プロパティ	価値	テスト基準
Water absorption, 23°C(73°F), immersion, equilibrium	1.6 %	ISO 62
Specific gravity, 23°C (73°F)	1.01 g/cm <sup>3</sup>	ISO 1183-1

## 包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

## 賞味期限


Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## PROCESSING CONDITIONS:

- 典型的な溶融温度 (最小 / 推奨 / 最大) - 射出成形: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- 典型的な金型温度 - 射出成形: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

# RILSAMID® AECV BLACK T8L

## DIAGRAMS



**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**