

TECHNICAL DATA SHEET

RILSAMID® AESN BLACK P110 TL

POLYAMIDE 12 PELLET

RILSAMID® AESN BLACK P110 TL is a polyamide 12 compound. This impact-modified grade is designed for tube extrusion and has improved hydrolysis resistance. It is a market standard to produce automotive cooling & selective catalyst reduction (SCR) lines.

Designation : ISO 16396 - PA12-L, EG1HL, C24-010

DESIGNATION

PA12-L

MAIN APPLICATIONS

- Auto - Water Cooling Circuit
- Auto - SCR Lines & Tanks

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

ADDITIVES

- Heat Stabilized
- Light Stabilized

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melt volume flow rate (MVR), 275°C / 5kg (527°F / 11 lb)	0.4 cm ³ /10min	ISO 1133

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Tensile modulus, 23°C (73°F), 1 mm/min	1120 / 1000 MPa	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 31 MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	18 / 18 %	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	>50 / >50 %	ISO 527-1/-2
Flexural modulus, 23°C (73°F)	- / 1016 MPa	ISO 178
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	- / 75 kJ/m ²	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 18 kJ/m ²	ISO 179 1eA

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditioned.

THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	176 °C	ISO 11357-1/-3

RILSAMID® AESN BLACK P110 TL

OTHER PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Specific gravity, 23°C (73°F)	1 g/cm ³	ISO 1183-1

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA