

TECHNICAL DATA SHEET

RILSAMID® AESN BLACK P201 TL

POLYAMIDE 12 PELLET

RILSAMID® AESN BLACK P201 TL is a polyamide 12 compound. This plasticized and impact-modified grade is designed for tube extrusion. It is a market standard to produce air brake tubing (PHLY) & automotive cooling lines.

Designation : ISO 16396 - PA12-IP, EG1HL, C22-007

DESIGNATION

PA12-IP

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

ADDITIVES

- Heat Stabilized
- Light Stabilized
- Plasticizer

RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Melt volume flow rate (MVR), 235°C / 5 kg (455°F / 11 lb)	5 cm ³ /10min	ISO 1133

MECHANICAL PROPERTIES

속성	DRY / COND VALUE*	테스트 표준
Tensile modulus, 23°C (73°F), 1 mm/min	580 / 580 MPa	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 30 MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 22 %	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	> 50 / > 50 %	ISO 527-1/-2
Flexural modulus, 23°C (73°F)	- / 450-600 MPa	ISO 178
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	No Break / No Break	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 7 kJ/m ²	ISO 179 1eA
Hardness, Shore D, 15 s	- / 64	ISO 868

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

RILSAMID® AESN BLACK P201 TL

속성	값	테스트 표준
Melting temperature, 10°C/min	176 °C	ISO 11357-1/-3

OTHER PROPERTIES

속성	값	테스트 표준
Specific gravity, 23°C (73°F)	1.01 g/cm ³	ISO 1183-1

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 21 kg / 44 lb bags
- 26 kg / 55 lb bags
- 455 kg / 1000 lb rigid containers
- 801 kg / 1760 lb rigid containers

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA