

## TECHNICAL DATA SHEET

# RILSAMID® AESN BLACK P202 CTL

## POLYAMIDE 12 PELLET

RILSAMID® AESN BLACK P202 CTL is a polyamide 12 compound. This plasticized and impact-modified electrostatic discharge (ESD) grade is specially designed for conductive multi-layer fuel line applications.

Designation : ISO 16396 - PA12-IP, EG1HLZ, C22-005

### DESIGNATION

PA12-IP

### MAIN APPLICATIONS

- Auto - Gasoline Lines

### DELIVERY FORM

- Pellets

### TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

### ADDITIVES

- Heat Stabilized
- Light Stabilized
- Plasticizer

## RHEOLOGICAL PROPERTIES

プロパティ	値	UNIT	テスト基準
Melt volume flow rate (MVR), 235°C / 5 kg (455°F / 11 lb)	1.2	cm <sup>3</sup> /10min	ISO 1133

## MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	UNIT	テスト基準
Tensile modulus, 23°C (73°F), 1 mm/min	620 / 620	MPa	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 35	MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 26	%	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50	%	ISO 527-1/-2
Flexural modulus, 23°C (73°F)	- / 568	MPa	ISO 178
Charpy unnotched impact strength, 23°C (73°F)	- / No Break		ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break		ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	- / 82	kJ/m <sup>2</sup>	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 4	kJ/m <sup>2</sup>	ISO 179 1eA
Hardness, Shore D, 15 s	- / 65		ISO 868

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

# RILSAMID® AESN BLACK P202 CTL

## THERMAL PROPERTIES

プロパティ	価値	UNIT	テスト基準
Melting temperature, 10°C/min	174	°C	ISO 11357-1/-3

## OTHER PROPERTIES

プロパティ	価値	UNIT	テスト基準
Specific gravity, 23°C (73°F)	1.14	g/cm <sup>3</sup>	ISO 1183-1

## 包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 20 kg / 44 lb bag
- 25 kg / 55 lb bag

## 賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## PROCESSING CONDITIONS:

- 典型的な熔融温度 (最小 / 推奨 / 最大) - 射出成形: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- 典型的な金型温度 - 射出成形: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

## SPECIAL CHARACTERISTICS

- Electrostatic discharge (ESD)

Headquarter: Arkema France  
51, ESPLANADE DU GÉNÉRAL DE GAULLE  
92800 PUTEAUX - LA DÉFENSE  
TÉL. : +33 (1) 49 00 90 00

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](http://arkema.com)

**ARKEMA**