

## TECHNICAL DATA SHEET

# RILSAMID® AESNO P40 TL

## POLYAMIDE 12 PELLET

RILSAMID® AESNO P40 TL is a polyamide 12 compound. This natural plasticized grade is designed for tube extrusion, including air brake tubing (PHL).

Designation : ISO 16396 - PA12-P, EG1HL, C22-004

### DESIGNATION

PA12-P

### MAIN APPLICATIONS

- Oil And Gas - Others
- Upstream - Offshore Umbilicals
- Cables Antitermites
- Performance Wire
- Cable Ties
- Hoses & Tubes - Pneumatics
- Hoses & Tubes
- Industry - Distribution
- Other Transportation
- Auto - Others Extrusion
- Heavy Truck - Air Brake Lines

### DELIVERY FORM

- Pellets

### TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

### ADDITIVES

- Heat Stabilized
- Light Stabilized

## RHEOLOGICAL PROPERTIES

プロパティ	価値	テスト基準
Melt volume flow rate (MVR), 235°C / 5 kg (455°F / 11 lb)	16 cm <sup>3</sup> /10min	ISO 1133

## MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	> 50 / > 50 %	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	24 / 26 %	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	26 / 23 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	430 / 380 MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	No Break / No Break	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 5 kJ/m <sup>2</sup>	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 390 MPa	ISO 178

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.

# RILSAMID® AESNO P40 TL

COND: Conditionned.

## THERMAL PROPERTIES

プロパティ	価値	テスト基準
Vicat softening temperature, 50N at 50°C/h	130 °C	ISO 306
Heat deflection temperature, 0.45 MPa	90 °C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa	46 °C	ISO 75-1/-2
Melting temperature, 10°C/min	174 °C	ISO 11357-1/-3

## ELECTRICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Surface resistivity, 23°C (73,4°F)	- / 5.0E+11 ohm/sq	IEC 62631-3-2
Volumic (transversal) resistivity, 23°C (73,4°F)	- / 1.0E+9 ohm/m	IEC 62631-3-1
Comparative tracking index, 23°C (73,4°F)	- / 600	IEC 60112
Dielectric stress, 23°C (73,4°F)	- / 24	IEC 60243-1

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

## OTHER PROPERTIES

プロパティ	価値	テスト基準
Water absorption, 23°C(73°F), immersion, equilibrium	1.2 %	ISO 62
Specific gravity, 23°C (73°F)	1.03 g/cm <sup>3</sup>	ISO 1183-1

## 包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

## 賞味期限






Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## PROCESSING CONDITIONS:

- 典型的な熔融温度 (最小 / 推奨 / 最大) - 射出成形: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- 典型的な金型温度 - 射出成形: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

# RILSAMID® AESNO P40 TL

## DIAGRAMS



**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790