

TECHNICAL DATA SHEET

RILSAMID® AZM 30 BLACK T6LD

POLYAMIDE 12 PELLET

RILSAMID® AZM 30 BLACK T6LD resin is a polyamide 12 compound. This glass fiber reinforced grade is designed for injection molding and is a market standard to produce automotive fittings & quick connectors.

Designation : ISO 16396 - PA12, GF30, M1G1HLR, C16-070

DESIGNATION

PA12-GF30

MAIN APPLICATIONS

- Auto - Fluid Connectors
- Heavy Truck - Air Brake Connectors

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Injection Molding

ADDITIVES

- Heat Stabilized
- Light Stabilized
- Release agent

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melt volume flow rate (MVR), 235°C / 5 kg (455°F / 11 lb)	7 cm ³ /10min	ISO 1133
Shrinkage, Parallel (t+24h)	0.2 %	ISO 294-4
Shrinkage, Normal (t+24h)	0.6 %	ISO 294-4

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Tensile modulus, 23°C (73°F), 1 mm/min	6700 / 6300 MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	3.4 / 3.4 %	ISO 527-1/-2
Charpy unnotched impact strength, 23°C (73°F)	79 / 77 kJ/m ²	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	83 / 83 kJ/m ²	ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	- / 19 kJ/m ²	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	12 / 12 kJ/m ²	ISO 179 1eA

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditioned.

RILSAMID® AZM 30 BLACK T6LD

THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	183 °C	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	165 °C	ISO 306
Heat deflection temperature, 0.45 MPa	176 °C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa	163 °C	ISO 75-1/-2
Yellow card available	yes	
Thermal degradation temperature, Under air at 10°C/min (1%_wt_Loss)	227 °C	ISO 11358-1
Thermal degradation temperature, Under nitrogen at 10°C/min (1%_wt_Loss)	224 °C	ISO 11358-1

ELECTRICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Surface resistivity, 23°C (73,4°F)	- / 1.0E+14 ohm/sq	IEC 62631-3-2
Volumic (transversal) resistivity, 23°C (73,4°F)	- / 1.0E+11 ohm/m	IEC 62631-3-1
Comparative tracking index, 23°C (73,4°F)	- / 600	IEC 60112
Dielectric stress, 23°C (73,4°F)	- / 35	IEC 60243-1
Relative permittivity, 100Hz	- / 4	IEC 60250
Relative permittivity, 1Mhz	- / 3	IEC 60250
Dissipation factor, 100Hz	- / 664	IEC 60250
Dissipation factor, 1Mhz	- / 664	IEC 60250

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

OTHER PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Specific gravity, 23°C (73°F)	1.24 g/cm ³	ISO 1183-1
Moisture absorption, At equilibrium at 23°C (73°F) / 50%HR	0.5 %	ISO 62
Water absorption, 23°C (73°F), immersion, equilibrium	1.3 %	ISO 62

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags
- 454 kg / 1000 lb rigid containers

SHELF LIFE





Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 250°C / 270°C / 290°C (480°F / 520°F / 555°F)
- Typical mold temperature - Injection molding: 40-90°C (105-195°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

RILSAMID® AZM 30 BLACK T6LD

DIAGRAMS



Headquarter: Arkema France
 420, rue d'Estienne d'Orves
 92705 Colombes Cedex – France
 T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
 Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

ARKEMA