

TECHNICAL DATA SHEET

RILSAMID® AZM 50 BLACK T6LD

POLYAMIDE 12 PELLET

RILSAN® AZM 50 BLACK T6LD is a polyamide 12 compound. This glass fiber reinforced grade is designed for injection molding and is used to produce air brake or automotive fittings & quick connectors, the incorporation of a high amount of glass fibers leading to a very rigid and tough product.

Designation : ISO 16396 - PA12, GF50, M1G1HLR, C16-120

DESIGNATION

PA12-GF50

MAIN APPLICATIONS

- Auto - Fluid Connectors
- Heavy Truck - Air Brake Connectors

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Injection Molding

ADDITIVES

- Heat Stabilized
- Light Stabilized
- Release agent

RHEOLOGICAL PROPERTIES

プロパティ	価値	テスト基準
Melt volume flow rate (MVR), 235°C / 5 kg (455°F / 11 lb)	6 cm ³ /10min	ISO 1133
Shrinkage, Parallel (t+24h)	0.2 %	ISO 294-4
Shrinkage, Normal (t+24h)	0.7 %	ISO 294-4

MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Tensile modulus, 23°C (73°F), 1 mm/min	12500 / 12000 MPa	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	153 / 145 MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	3.8 / 3.6 %	ISO 527-1/-2
Stress at break, 23°C (73°F), 50 mm/min	152 / 144 MPa	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	4.6 / 4.9 %	ISO 527-1/-2
Flexural modulus, 23°C (73°F)	- / 8300 MPa	ISO 178
Charpy unnotched impact strength, 23°C (73°F)	84 / 80 kJ/m ²	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	90 / 84 kJ/m ²	ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	- / 22 kJ/m ²	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	15 / 15 kJ/m ²	ISO 179 1eA

RILSAMID® AZM 50 BLACK T6LD

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

THERMAL PROPERTIES

プロパティ	価値	テスト基準
Melting temperature, 10°C/min	175 °C	ISO 11357-1/-3
Thermal Degradation temperature, Under air at 10°C/min (1%_wt_Loss)	224 °C	ISO 11358-1
Thermal Degradation temperature, Under nitrogen at 10°C/min (1%_wt_Loss)	224 °C	ISO 11358-1

OTHER PROPERTIES

プロパティ	価値	テスト基準
Specific gravity, 23°C (73°F)	1.47 g/cm ³	ISO 1183-1

包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

賞味期限

Six months from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- 典型的な熔融温度 (最小 / 推奨 / 最大) - 射出成形: 270°C / 285°C / 300°C (520°F / 545°F / 570°F)
- 典型的な金型温度 - 射出成形: 40-90°C (105-195°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

REGIONAL AVAILABILITY

Asia Pacific, Europe, Northern America

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA