

TECHNICAL DATA SHEET

RILSAN® BESN BLACK P123 TL

POLYAMIDE 11 PELLET

RILSAN® BESN BLACK P123 TL is a polyamide 11 compound. It is produced from a renewable & sustainable source (castor oil). This impact-modified grade is designed for tube extrusion and has improved hydrolysis resistance. It is a market reference to produce automotive cooling & selective catalyst reduction (SCR) lines.

Designation : ISO 16396 - PA 11-IP, EG1HL, C18-007

TYPE

PA11-I

MAIN APPLICATIONS

- Auto Battery Cooling
- Auto Enging Cooling
- Auto - SCR Lines & Tanks
- Heavy Truck H2 & Gas Lines And Tanks
- Heavy Truck - Air Brake Lines

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

ADDITIVES

- Heat Stabilized
- Light Stabilized

MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	UNIT	テスト基準
Yield stress, 23°C (73°F), 50 mm/min	23 / 23	MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	25 / 25	%	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	> 50 / > 50	%	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 100	kJ/m2	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 25	kJ/m2	ISO 179 1eA

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

THERMAL PROPERTIES

プロパティ	価値	UNIT	テスト基準
Melting temperature, 10°C/min	189	°C	ISO 11357-1/-3

OTHER PROPERTIES

プロパティ	価値	UNIT	テスト基準
Specific gravity, 23°C (73°F)	1	g/cm³	ISO 1183-1

RILSAN® BESN BLACK P123 TL

包装

Available packaging:

- 25 kg / 55 lb 袋

賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- 典型的な熔融温度 (最小 / 推奨 / 最大) - 射出成形: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- 典型的な金型温度 - 射出成形: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

SPECIAL CHARACTERISTICS

- Bio-based
- Low oligomers

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

