

TECHNICAL DATA SHEET

RILSAN® BESNO P210 TL

POLYAMIDE 11 PELLET

RILSAN® BESNO P210 TL is a polyamide 11 compound. It is produced from a renewable & sustainable source (castor oil). This natural plasticized & impact-modified grade is designed for tube extrusion.

Designation : ISO 16396 - PA11-IP, EG1HL, C22-007

DESIGNATION

PA11-IP

MAIN APPLICATIONS

- Auto - Diesel Lines
- Auto - Gasoline Lines

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

ADDITIVES

- Heat Stabilized
- Light Stabilized
- Plasticizer

MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Hardness, Shore D, 15 s	- / 67	ISO 868
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50 %	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 35 %	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	30 / 30 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	510 / 510 MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	No Break / No Break	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 9 kJ/m2	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 500 MPa	ISO 178

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

THERMAL PROPERTIES

プロパティ	価値	テスト基準
Melting temperature, 10°C/min	184 °C	ISO 11357-1/-3

RILSAN® BESNO P210 TL

OTHER PROPERTIES

プロパティ	価値	テスト基準
Specific gravity, 23°C (73°F)	1.03 g/cm ³	ISO 1183-1

包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- 典型的な溶融温度 (最小 / 推奨 / 最大) - 射出成形: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- 典型的な金型温度 - 射出成形: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

SPECIAL CHARACTERISTICS

- Bio-based
- Low oligomers

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA