

TECHNICAL DATA SHEET

RILSAN® BESNO P40 W6 TL

POLYAMIDE 11 PELLET

RILSAN® BESNO P40 W6 TL is a polyamide 11 compound. It is produced from a renewable & sustainable source (castor oil). This natural plasticized grade is designed for tube extrusion. It is classified as Halogen Free Flame Retardant (HFFR).

Designation : ISO 16396 - PA11-P, EFHL, C22-005

DESIGNATION

PA11-P

MAIN APPLICATIONS

- Hoses & Tubes
- Industry - Distribution

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

ADDITIVES

- Flame retarding agent
- Heat Stabilized
- Light Stabilized
- Plasticizer

MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50 %	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 41 %	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 24 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	- / 540 MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 25 kJ/m2	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 7 kJ/m2	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 470 MPa	ISO 178

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

RILSAN® BESNO P40 W6 TL

THERMAL PROPERTIES

プロパティ	価値	テスト基準
Yellow card available	yes	
Heat deflection temperature, 0.45 MPa	130 °C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa	47 °C	ISO 75-1/-2
Melting temperature, 10°C/min	180 °C	ISO 11357-1/-3

OTHER PROPERTIES

プロパティ	価値	テスト基準
Specific gravity, 23°C (73°F)	1.11 g/cm ³	ISO 1183-1

包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- 典型的な溶融温度 (最小 / 推奨 / 最大) - 射出成形: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- 典型的な金型温度 - 射出成形: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

SPECIAL CHARACTERISTICS

- Bio-based
- Halogen Free Flame Retardant (HFFR)
- Low oligomers

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA