

## TECHNICAL DATA SHEET

# RILSAN® BLACK RDP 15-10 ES

## POLYAMIDE 11 POWDER

RILSAN® electrostatic spray powders are thermoplastic polyamides obtained from renewable resources.

Outstanding characteristics: abrasion resistance, corrosion resistance, impact resistance, sound reduction, flexibility, low coefficient of friction.

### Designation

- PA11

### MAIN APPLICATIONS

- Powder Coating - Others

### Delivery Form

- Powder

### Transformation Processes

- Electrostatic spraying

### Additives

- Heat Stabilized

## MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Coating impact, 23°C (73°F)	- / 160 J	ASTM D2794
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 15 mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

## THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	183-188 °C	ISO 11357-1/-3

## OTHER PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Particle Size Distribution (PSD) (Coarse particles > 75 µm)	2.5 %	
Particle Size Distribution (PSD) (Coarse particles > 106 µm)	0.5 %	
Particle Size Distribution (PSD) (Coarse particles > 150 µm)	0.2 %	
Approximate RAL number	9005	
Covering Efficiency (120 µm)	0.14 kg/m <sup>2</sup>	Internal Arkema
Specific gravity of coating, 20°C (68°F)	1.12 g/cm <sup>3</sup>	ISO 1183-1
Median particles (D50)	30 µm	ISO 13320

# RILSAN® BLACK RDP 15-10 ES

## 賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## SPECIAL CHARACTERISTICS

- Bio-based

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**