

# TECHNICAL DATA SHEET RILSAN® BLACK RDP 15-10 ES

# **POLYAMIDE 11 POWDER**

RILSAN® electrostatic spray powders are thermoplastic polyamides obtained from renewable resources.

Outstanding characteristics: abrasion resistance, corrosion resistance, impact resistance, sound reduction, flexibility, low coefficient of friction.

## **DESIGNATION**

**PA11** 

#### MAIN APPLICATIONS

· Powder Coating - Others

#### **DELIVERY FORM**

Powder

## TRANSFORMATION PROCESSES

· Electrostatic spraying

#### **ADDITIVES**

Heat Stabilized

# **MECHANICAL PROPERTIES**

プロバティ	DRY / COND VALUE*	テスト基準
Coating impact, 23°C (73°F)	- / 160 J	ASTM D2794
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 15 mg	ISO 9352

<sup>\*</sup>DRY: Dry As Molded (DAM) if pellet / Dry if powder. COND: Conditionned.

# THERMAL PROPERTIES

プロパティ	価値	テスト基準
Melting temperature, 10°C/min	183-188 °C (366.8 °F)	ISO 11357-1/-3

## OTHER PROPERTIES

プロパティ	価値	テスト基準
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Particle Size Distribution (PSD) (Coarse particles > 75 μm)	2.5 %	
Particle Size Distribution (PSD) (Coarse particles > 106 μm)	0.5 %	
Particle Size Distribution (PSD) (Coarse particles > 150 μm)	0.2 %	
Approximate RAL number	9005	
Covering Efficiency (120 µm)	0.14 kg/m²	Internal Arkema
Specific gravity of coating, 20°C (68°F)	1.12 g/cm³	ISO 1183-1
Median particles (D50)	30 µm	ISO 13320



# RILSAN® BLACK RDP 15-10 ES

# 包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

• 45 kg / 100 lb drums

# 賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## SPECIAL CHARACTERISTICS

· Bio-based

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

