

TECHNICAL DATA SHEET

RILSAN® BMNO SG FILAGE

POLYAMIDE 11 PELLET

RILSAN® BMNO SG FILAGE is a polyamide 11 resin. It is produced from a renewable & sustainable source (castor oil). This natural grade is particularly suitable for textile applications.

Designation : ISO 16396 - PA11, M, C12-010

DESIGNATION

PA11

MAIN APPLICATIONS

- Monofilament
- Industry - Distribution

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Filament extrusion
- Scattering, paste, double dot

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Shrinkage, Normal (t+24h)	0.9 %	ISO 294-4
Shrinkage, Parallel (t+24h)	1.1 %	ISO 294-4
Melt volume flow rate (MVR), 235°C / 2.16 kg (455°F / 4.4 lb)	30 cm ³ /10min	ISO 1133

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Hardness, Shore D, 15 s	- / 68	ISO 868
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50 %	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 5 %	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 41 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	1280 / 1280 MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 8.3 kJ/m ²	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 10.5 kJ/m ²	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 1140 MPa	ISO 178

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditioned.

THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	189 °C	ISO 11357-1/-3

RILSAN® BMNO SG FILAGE

OTHER PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Bio-based carbon content, Measured	98 %	ASTM D6866
Water absorption, 23°C (73°F), immersion, equilibrium	1.9 %	ISO 62
Specific gravity, 23°C (73°F)	1.03 g/cm ³	ISO 1183-1

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 210°C / 230°C / 260°C (410°F / 445°F / 500°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

SPECIAL CHARACTERISTICS

- Bio-based
- Low oligomers

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA