

TECHNICAL DATA SHEET RILSAN® BMNO

POLYAMIDE 11 PELLET

RILSAN® BMNO is a polyamide 11 resin. It is produced from a renewable & sustainable source (castor oil). This natural grade contains no additive and is specially designed for food contact application

Designation : ISO 16396 - PA11, M, C12-010

DESIGNATION

PA11

MAIN APPLICATIONS

- Battery - Others Energies
- Accessories
- Home Appliance
- Compounding
- Industry - Distribution
- Other Transportation
- Auto - Others Injection

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Injection Molding

RHEOLOGICAL PROPERTIES

プロパティ	価値	テスト基準
Shrinkage, Normal (t+24h)	0.9 %	ISO 294-4
Shrinkage, Parallel (t+24h)	1.1 %	ISO 294-4
Melt volume flow rate (MVR), 235°C / 2.16 kg (455°F / 4.4 lb)	30 cm ³ /10min	ISO 1133

MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Hardness, Shore D, 15 s	- / 68	ISO 868
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50 %	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 5 %	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 41 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	- / 1280 MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 8.3 kJ/m ²	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 10.5 kJ/m ²	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 1140 MPa	ISO 178

RILSAN® BMNO

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

THERMAL PROPERTIES

プロパティ	価値	テスト基準
Yellow card available	yes	
Heat deflection temperature, 0.45 MPa	145 °C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa	50 °C	ISO 75-1/-2
Melting temperature, 10°C/min	189 °C	ISO 11357-1/-3

OTHER PROPERTIES

プロパティ	価値	テスト基準
Bio-based carbon content, Measured	98 %	ASTM D6866
Water absorption, 23°C(73°F), immersion, equilibrium	1.9 %	ISO 62
Specific gravity, 23°C (73°F)	1.03 g/cm ³	ISO 1183-1

包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- 典型的な溶融温度 (最小 / 推奨 / 最大) - 射出成形: 210°C / 230°C / 260°C (410°F / 445°F / 500°F)
- 典型的な金型温度 - 射出成形: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

SPECIAL CHARACTERISTICS

- Bio-based
- Low oligomers

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA