

TECHNICAL DATA SHEET

RILSAN® BMVO TLD

POLYAMIDE 11 PELLET

RILSAN® BMVO TLD is a polyamide 11 compound. RILSAN® BMVO TLD is a polyamide 11 compound produced from a renewable & sustainable source (castor oil). This natural grade is designed for injection molding and is used to produce automotive fittings & quick connectors.

Designation : ISO 16396 - PA11, M1G1HLR, C18-010

DESIGNATION

PA11

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Injection Molding

ADDITIVES

- Heat Stabilized
- Light Stabilized
- Release agent

RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Shrinkage, Parallel (t+24h)	1.4 %	ISO 294-4
Shrinkage, Normal (t+24h)	1.5 %	ISO 294-4

MECHANICAL PROPERTIES

속성	DRY / COND VALUE*	테스트 표준
Tensile modulus, 23°C (73°F), 1 mm/min	1320 / 1260 MPa	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 42 MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 5 %	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50 %	ISO 527-1/-2
Flexural modulus, 23°C (73°F)	- / 1145 MPa	ISO 178
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	- / 12 kJ/m2	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 10 kJ/m2	ISO 179 1eA
Hardness, Shore D, 15 s	- / 71	ISO 868

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

RILSAN® BMVO TLD

속성	값	테스트 표준
Melting temperature, 10°C/min	189 °C	ISO 11357-1/-3

OTHER PROPERTIES

속성	값	테스트 표준
Specific gravity, 23°C (73°F)	1.03 g/cm ³	ISO 1183-1

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 26 kg / 55 lb bags

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 250°C / 270°C / 290°C (480°F / 520°F / 555°F)
- Typical mold temperature - Injection molding: 40-90°C (105-195°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

SPECIAL CHARACTERISTICS

- Bio-based
- Low oligomers

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA