

## TECHNICAL DATA SHEET

# RILSAN® BUM 30 BLACK

## POLYAMIDE 11 PELLET

RILSAN® BUM 30 BLACK is a polyamide 11 compound. It is produced from a renewable & sustainable source (castor oil). This reinforced grade is designed for injection molding, the incorporation of glass beads yielding a virtually isotropic reinforced product.

Designation : ISO 16396 - PA11, GB30, M1G1HLR, C18-020

### DESIGNATION

PA11-GB30

### MAIN APPLICATIONS

- Industry - Distribution
- Auto - Fluid Connectors

### DELIVERY FORM

- Pellets

### TRANSFORMATION PROCESSES

- Injection Molding

## RHEOLOGICAL PROPERTIES

プロパティ	価値	テスト基準
Shrinkage, Parallel (t+24h)	1.8 %	ISO 294-4
Shrinkage, Normal (t+24h)	1.6 %	ISO 294-4
Melt volume flow rate (MVR), 235°C / 5 kg (455°F / 11 lb)	20 cm <sup>3</sup> /10min	ISO 1133

## MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Hardness, Shore D, 15 s	- / 71	ISO 868
Charpy unnotched impact strength, 23°C (73°F)	- / 96 kJ/m <sup>2</sup>	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / 96 kJ/m <sup>2</sup>	ISO 179 1eU
Tensile modulus, 23°C (73°F), 1 mm/min	1850 / 1850 MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 6 kJ/m <sup>2</sup>	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 5 kJ/m <sup>2</sup>	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 1600 MPa	ISO 178

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

## THERMAL PROPERTIES

プロパティ	価値	テスト基準
Melting temperature, 10°C/min	189 °C	ISO 11357-1/-3

# RILSAN® BUM 30 BLACK

## OTHER PROPERTIES

プロパティ	価値	テスト基準
Specific gravity, 23°C (73°F)	1.23 g/cm <sup>3</sup>	ISO 1183-1

## 包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

## 賞味期限

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## PROCESSING CONDITIONS:

- 典型的な熔融温度 (最小 / 推奨 / 最大) - 射出成形: 250°C / 270°C / 290°C (480°F / 520°F / 555°F)
- 典型的な金型温度 - 射出成形: 40-90°C (105-195°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

## SPECIAL CHARACTERISTICS

- Bio-based
- Low oligomers

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**