

## TECHNICAL DATA SHEET

# RILSAN® BZM 30 BLACK TL

## POLYAMIDE 11 PELLET

RILSAN® BZM 30 BLACK TL is a polyamide 11 compound. It is produced from a renewable & sustainable source (castor oil). This glass fiber reinforced grade is designed for injection molding and is a market reference to produce air brake or automotive fittings & quick connectors.

Designation : ISO 16396 - PA11, GF30, M1G1HLR, C18-070

### DESIGNATION

PA11-GF30

### DELIVERY FORM

- Pellets

### TRANSFORMATION PROCESSES

- Injection Molding

### ADDITIVES

- Heat Stabilized
- Light Stabilized

## RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Shrinkage, Parallel (t+24h)	0.3 %	ISO 294-4
Shrinkage, Normal (t+24h)	0.7 %	ISO 294-4
Melt volume flow rate (MVR), 235°C / 5 kg (455°F / 11 lb)	7 cm <sup>3</sup> /10min	ISO 1133

## MECHANICAL PROPERTIES

속성	DRY / COND VALUE*	테스트 표준
Tensile modulus, 23°C (73°F), 1 mm/min	6300 / 6300 MPa	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	6 / 7.5 %	ISO 527-1/-2
Flexural modulus, 23°C (73°F)	- / 5640 MPa	ISO 178
Charpy unnotched impact strength, 23°C (73°F)	- / 74 kJ/m <sup>2</sup>	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / 83 kJ/m <sup>2</sup>	ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	- / 20 kJ/m <sup>2</sup>	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 11 kJ/m <sup>2</sup>	ISO 179 1eA
Hardness, Shore D, 15 s	- / 74	ISO 868

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

속성	값	테스트 표준
Melting temperature, 10°C/min	189 °C	ISO 11357-1/-3

# RILSAN® BZM 30 BLACK TL

## OTHER PROPERTIES

속성	값	테스트 표준
Specific gravity, 23°C (73°F)	1.25 g/cm <sup>3</sup>	ISO 1183-1
Water absorption, 23°C (73°F), immersion, equilibrium	1.3 %	ISO 62

## PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 26 kg / 55 lb bags

## SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 250°C / 270°C / 290°C (480°F / 520°F / 555°F)
- Typical mold temperature - Injection molding: 40-90°C (105-195°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

## SPECIAL CHARACTERISTICS

- Bio-based
- Low oligomers

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**