

## TECHNICAL DATA SHEET

# RILSAN® EVOLUTION ENO P210 TL

## POLYAMIDE ALLOY PELLET

RILSAN® EVOLUTION ENO P210 TL is a polyamide 11 compound. It is partially produced from a renewable & sustainable source (castor oil). This grade is designed for high pressure fuel contact applications.

### DESIGNATION

PA\*

### DELIVERY FORM

- Pellets

### TRANSFORMATION PROCESSES

- Tube Extrusion

### ADDITIVES

- Heat Stabilized
- Light Stabilized
- Plasticizer

## MECHANICAL PROPERTIES

속성	DRY / COND VALUE*	테스트 표준
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Yield strain, 23°C (73°F), 50 mm/min	- / 39 %	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	32 / 32 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	400 / 400 MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 24 kJ/m <sup>2</sup>	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 3 kJ/m <sup>2</sup>	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 450 MPa	ISO 178

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

속성	값	테스트 표준
Melting temperature, 10°C/min	215 °C	ISO 11357-1/-3

## OTHER PROPERTIES

속성	값	테스트 표준
Specific gravity, 23°C (73°F)	1.08 g/cm <sup>3</sup>	ISO 1183-1

## PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 26 kg / 55 lb bags

# RILSAN® EVOLUTION ENO P210 TL

## SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 250°C / 270°C / 290°C (480°F / 520°F / 555°F)
- Typical mold temperature - Injection molding: 40-90°C (105-195°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

## SPECIAL CHARACTERISTICS

- Bio-based

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**